

Technical data sheet - flooring

Technical data		
Reaction to fire	EN 13501	Bfl-S1(Hardly flammable)
Formaldehyde emission	EN 717-1	E1
Brinell hardness	EN 1534	10 HB (Average value)
Thermal resistance	EN 12664 / 12667	R 0.07 (m ² x K)/W
Impact resistance	EN 14354:2017	EC3*
Thickness swell	EN 13329:2017 / ISO 24336	Class 34 (< 8%)

*Applies only to laquered flooring

Installation	
Installation method	Floating installation, Välinge 2G/5G®
Installation instructions	Download from www.woodura.se/downloads
Underlayment material	Foam with CS > 60 kPa & CC > 5 kPa (According to CEN / TS 16354)
Care & Maintenance instructions	Download from www.woodura.se/downloads

Size and package	11 x 187 x 2000 mm	11 x 210 x 2379 mm	11 x 276 x 2379 mm
Thickness (mm)	11.3	11.3	11.3
Width (mm)	187	210	276
Length (mm)	2000	2379	2379
Wear layer thickness (mm)	0.6	0.6	0.6
Boards / box	5	4	3
m ² / box	1.87	2.00	1.97
m ² / pallet	102.85	96.00	94.56
Weight / m ² (kg)	10	10	10
Weight / box (kg)	18.5	19.8	19.5

Due to the nature of the material this table shows typical values.